

Electrical Steel Sheets : : Special Electrical Steel Sheet

JAPAN JFE(JNEH) CORE

| Grade | | Assumed Density (kg/dm ³) | Core Loss (w/kg) | Magnetic Flux Density (T) | Lamination Factor (%) |
|------------|-------------------|--|---------------------|------------------------------|--------------------------|
| Symbol | Thickness (mm) | | W 10/400 | B50 | |
| 20JNEH1200 | 0.20 | 7.65 | 12.00 | 1.62 | 93.0 |
| 20JNEH1500 | 0.20 | 7.65 | 15.00 | 1.63 | |